



MgO

SPECIFICATION

Items	MgO%≥	CaO%≤	Fe2O3%≤	Al2O3%≤	SiO2%≤	LOI%≤
MgO-94	94.0	3.0	1.0	1.0	4.0	6.0
MgO-92	92.0	3.0	1.0	1.0	4.0	6.0
MgO-90	90.0	3.0	1.0	1.0	4.0	6.0
MgO-87	87.0	3.5	1.0	1.0	4.0	7.0
MgO-85	85.0	4.0	1.0	1.0	4.0	7.0
MgO-83	83.0	5.0	1.0	1.0	8.0	6.0
MgO-80	80.0	5.5	1.0	1.0	10.0	8.0
MgO-75	75.0	7.5	1.0	1.0	10.0	10.0
MgO-70	70.0	8.0	1.5	1.0	12.0	12.0
MgO-65	65.0	10.0	1.5	1.0	14.0	16.0
MgO-60	60.0	10.0	1.5	1.0	15.0	18.0

CIQ Test Item	Testing Result	PPM	Test Method
Pb	4.0	PPM	LFBK-130
As	0.9	PPM	LFBK-130
Hg	N.D	PPM	LFBK-130
Cd	0.05	PPM	LFBK-130
F	375	PPM	LFBK-130
H2O	0.52	%	GB/T2007-1987

Size: 0-0.3mm, 0.3-2.0mm, 60 mesh, 120 mesh, 200mesh, 325 mesh, granular